

C4

- Colonna senza testa
- Not headed pillar



Materiale: 1.7131


Material: 1.7131

Trattamento termico: Cementazione + Tempra

Heat treatment: Cementing + hardening

Durezza: HRC 61 - 63

Hardness: HRC 61 - 63



Esempio di ordinativo: C4 D1xL
Example of purchasing order: C4 D1xL

D1	L																		L1	
	85	95	105	115	125	135	145	155	170	185	200	225	250	275	300	325	350	400		
15 - 16	•	•	•	•	•	•	•	•												16
17 - 18	•	•	•	•																18
19 - 20	•	•	•																	20
24 - 25				•	•	•														25
30 - 31				•	•	•	•	•												30
40 - 41							•	•	•	•	•									40
50 - 51									•	•	•	•	•	•	•	•	•	•	•	50
63												•	•	•	•		•	•		63